



### ULTIMA 30

Ultima 30 Film is a microperforated adhesive on which a high print quality can be produced. It is suitable for both automotive bodies and glass surfaces. Thanks to its structure, a maximum brightness is maintained (30% VLT). Its white printable side protects you from prying eyes and the black inside allows you to always have a perfect outward view.



Tintfit Window Films warranty  
**2 YEARS**



Fire-resistance rating  
**MI**



Storage from -5°C to +40°C  
**3 YEARS**



REACH RoHS compliant  
**RESPECTED**


### TECHNICAL DATASHEET

Data calculated based on film applied to clear glass 3 mm thick (\*on double glazing 4-16-4)

Ultraviolet transmission	50 %
Visible light transmission	30 %
Reflection of external visible light	55 %
Reflection of internal visible light	7 %
Total solar energy rejected	55 %
Total solar energy rejected 2*	48 %
Solar ratio :	
Solar energy reflection	51 %
Solar energy absorption	20 %
Solar energy transmission	30 %
Reduction in Solar Glare	50 %
g-value	0,44
u-value	-
Shading coefficient	0,5
Installation type : Internal application +	
External application	
Roll length	30,5 m
PET / PVC composition	PVC
Thickness	140 µ
Colour : WHITE	

### CONSTRUCTION

1. 100µ monomer PVC
2. Half Permanent Adhesive, allowing the "degassing" of the actual surface, and limits the adhesive transfer during removal
3. Protection release liner, disposable after installation



### MAINTENANCE INSTRUCTIONS

Soapy water solution, do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

*Non-contractual data, Tintfit Window Films reserves the right to modify the composition of its films at any time.*

### INSTALLATION ADVICE

Vertical installation and on standard glass surface\*\*

Clear single pane	✓
Tinted single pane	✓
Reflective tinted single pane	✓
Clear double pane	✓
Tinted double pane	✓
Reflective tinted double pane	✓
Gas-filled double pane - Low E	✓
STADIP EXT. clear double pane	✓
STADIP INT. clear double pane	✓

✓ Yes ! Caution ✗ Not recommended

\*\*Recommendations provided on the basis of a glazed surface covering up to 2.5m<sup>2</sup>.