



REFLECTIVE SILVER 20 STATIC

Reflective Silver 20 Static films are highly effective at reducing solar heat gain, whilst at the same time continuing to allow most natural light to pass through. Solar glare is greatly diminished and its one-way mirror aspect guarantees privacy from prying eyes, whilst affording a modern feel to the exterior of a building. In addition, this "static" version is easy to install.



Tintfit Window Films warranty

5 YEARS



Storage from -5°C to +40°C

3 YEARS



REACH RoHS compliant

RESPECTED

TECHNICAL DATASHEET

Data calculated based on film applied to clear glass 3 mm thick (*on double glazing 4-16-4)

Ultraviolet transmission	18 %
Visible light transmission	24 %
Reflection of external visible light	60 %
Reflection of internal visible light	60 %
Total solar energy rejected	79 %
Total solar energy rejected 2*	75 %
Solar ratio :	
Solar energy reflection	55 %
Solar energy absorption	33 %
Solar energy transmission	12 %
Reduction in Solar Glare	83 %
g-value	0.20
u-value	5.1
Shading coefficient	0.22
Installation type :	
Roll length	20 m
PET / PVC composition	PET + PVC
Thickness	100 µ

Colour : SILVER

CONSTRUCTION

1. High optical quality polyester
2. Bonding adhesive
3. PVC with anti IR metal particles deposit
4. Protection liner, disposable after installation

MAINTENANCE INSTRUCTIONS

Soapy water solution, do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

Non-contractual data, Tintfit Window Films reserves the right to modify the composition of its films at any time.

INSTALLATION ADVICE

Vertical installation and on standard glass surface**

Clear single pane	✓
Tinted single pane	✓
Reflective tinted single pane	✓
Clear double pane	!
Tinted double pane	✗
Reflective tinted double pane	!
Gas-filled double pane - Low E	!
STADIP EXT. clear double pane	!
STADIP INT. clear double pane	✗

✓ Yes ! Caution ✗ Not recommended

*Recommendations provided on the basis of a glazed surface covering up to 2.5m², contact us for definitive details or to obtain a thermal check analysis report.