



EXT. REFLECTIVE PRIVACY 01

External Reflective Privacy 01 is highly effective at reducing solar heat gain, whilst at the same time continuing to allow some natural light transmission. This film provides effective protection against solar glare, whilst its one-way mirror aspect further guarantees privacy from prying eyes. Its modern design immediately gives a contemporary feel to any building exterior.



Tintfit Window Films warranty
10 YEARS



Fire-resistance rating
M1



Storage from -5°C to +40°C
3 YEARS



REACH RoHS compliant
RESPECTED

TECHNICAL DATASHEET


Data calculated based on film applied to clear glass 3 mm thick (*on double glazing 4-16-4)

Ultraviolet transmission	1 %
Visible light transmission	< 1 %
Reflection of external visible light	88 %
Reflection of internal visible light	11 %
Total solar energy rejected	99 %
Total solar energy rejected 2*	99 %
Solar ratio :	
Solar energy reflection	85 %
Solar energy absorption	14 %
Solar energy transmission	1 %
Reduction in Solar Glare	100 %
g-value	0.03
u-value	5.1
Shading coefficient	0.2
Installation type : External application	
Roll length	30,5 m
PET / PVC composition	PET
Thickness	60 µ

Colour : SILVER

CONSTRUCTION

1. "Hard" scratch resistant layer, for durability and ease of maintenance during window cleaning
2. Dyed polyester without optical distortion
3. Bonding adhesive
4. High optical quality polyester, with anti IR metal particles deposit
5. PS adhesive, glass polymerization within 15 days
6. Protection release liner, disposable after installation



MAINTENANCE INSTRUCTIONS

Soapy water solution, do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

Non-contractual data, Tintfit Window Films reserves the right to modify the composition of its films at any time.

INSTALLATION ADVICE

Vertical installation and on standard glass surface**

Clear single pane	✓
Tinted single pane	✓
Reflective tinted single pane	✓
Clear double pane	✓
Tinted double pane	✓
Reflective tinted double pane	✓
Gas-filled double pane - Low E	✓
STADIP EXT. clear double pane	✓
STADIP INT. clear double pane	✓

✓ Yes ! Caution ✗ Not recommended

*Recommendations provided on the basis of a glazed surface covering up to 2.5m², contact us for definitive details or to obtain a thermal chock analysis report.