



SPECTRA 60

Spectra 60 is carefully designed to act selectively on the spectrum of solar light, offering the best possible compromise between transparency and performance.



Tintfit Window Films warranty
10 YEARS



Fire-resistance rating
M1



Storage from -5°C to +40°C
3 YEARS



European Standard EN 1096-1
**TESTED IN A
LABORATORY**



REACH RoHS compliant
RESPECTED

TECHNICAL DATASHEET


Data calculated based on film applied to clear glass 3 mm thick (*on double glazing 4-16-4)

Ultraviolet transmission	1 %
Visible light transmission	62 %
Reflection of external visible light	14 %
Reflection of internal visible light	14 %
Total solar energy rejected	57 %
Total solar energy rejected 2	54 %
Solar ratio :	
Solar energy reflection	34 %
Solar energy absorption	29 %
Solar energy transmission	37 %
Reduction in Solar Glare	34 %
g-value	0.44
u-value	4.9
Rejected Infrared (760-2500 nm)	+/- 80 %
Shading coefficient	0.5
Installation type : Internal application	
Roll length	30,5 m
PET / PVC composition	PET
Thickness	40 µ

Colour : LIGHT CHAMPAGNE

CONSTRUCTION

1. "Hard" scratch resistant layer, for durability and ease of maintenance during window cleaning
2. High optical quality polyester, with anti IR metal particles deposit
3. Bonding adhesive
4. High optical quality polyester
5. PS adhesive, glass polymerization within 15 days
6. Protection release liner, disposable after installation



MAINTENANCE INSTRUCTIONS

Soapy water solution, do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

Non-contractual data, Tintfit Window Films reserves the right to modify the composition of its films at any time.

INSTALLATION ADVICE

Vertical installation and on standard glass surface*

Clear single pane	✓
Tinted single pane	✓
Reflective tinted single pane	✓
Clear double pane	✓
Tinted double pane	✓
Reflective tinted double pane	✓
Gas-filled double pane - Low E	!
STADIP EXT. clear double pane	✓
STADIP INT. clear double pane	!

✓ Yes ! Caution ✗ No

*Recommendations provided on the basis of a glazed surface covering up to 2.5m², contact us for definitive details or to obtain a thermal chock analysis report.